

PRODUCT	DESCRIPTION	VISCOSITY (cP)*	THIX INDEX	GEL TIME (min)	Promotor / Accelerator (% m/m)	Organic Peroxide Catalyst (% m/m)	HDT (°C)
Poolcoats							
PCPOL-F210-CLRBRU	Polijel 210 Topcoat ISO/NPG Clear Brush	5500-6500	-	8-16	PA	1.0	90
PCPOL-F210-WHTBRU	Polijel 210 Topcoat ISO/NPG White Brush	5500-6500	-	8-16	PA	1.0	90
PCPOLF210SKYBLUBR	Polijel 210 Topcoat ISO/NPG Sky Blue 856 Brush	5500-6500	-	8-16	PA	1.0	90

PA = Pre-accelerated