

PRODUCT	DESCRIPTION	VISCOSITY (cP)*	THIX INDEX	GEL TIME (min)	Promotor / Accelerator (% m/m)	Organic Peroxide Catalyst (% m/m)	HDT (°C)
<b>Chemically Resistant Resin Systems</b>							
VESWA-SW901	Swancor Bisphenol-a Vinyl Ester Resin	350-550	-	15-25	0.4%-Co6%, 0.05%DMA	1.2	108-112
VESWA-SW901-200	Swancor Bisphenol-a Vinyl Ester Resin	150-250	-	15-25	0.4%-Co6%, 0.05%DMA	1.2	102-105
VESWA-SW907-1	Swancor Novalac Epoxy Vinyl Ester Resin	270-400	-	20-30	0.4%-Co6%, 0.05%DMA	1.2	144-150

\*Refer to Technical Data sheet for methods  
HDT: Method ISO 0075-B