

PRODUCT	DESCRIPTION	VISCOSITY (cP)*	GEL TIME (MIN)	PROMOTER/ACCELERATOR	ORGANIC PEROXIDE	HDT
---------	-------------	-----------------	----------------	----------------------	------------------	-----

ORTHOPHTHALLIC/ GENERAL PURPOSE LAMINATING RESINS

UPPOL-3404TA-H30	ORTHO, FAST WET-OUT, MEDIUM REACTIVE THIXOTROPIC LAMINATING	500-600	1.3-1.6	PA	1.0	62
UPPOL-3877TA H30	TEREPHTHALIC FAST WET-OUT, THIXOTROPIC LAMINATING	400-500	1.3-1.5	PA	1.0	82
UPPOL-3401TA-H30	ORTHO, MEDIUM REACTIVE THIXOTROPIC LAMINATING	850-950	1.1-1.3	PA	1.0	65
UPPOL-3562-230	ORTHO, MEDIUM REACTIVE, UNACCELERATED, NON THIX, LAMINATING	250-350	-	1% (1% CO OCT)	1.0	86

* REFER TO TECHNICAL DATA SHEET FOR METHODS

PA + PRE-ACCELERATED

HDT : METHOD ISO 0075-B