

PRODUCT	DESCRIPTION	VISCOSITY (cP)*	GEL TIME (MIN)	PROMOTER/ACCELERATOR	ORGANIC PEROXIDE	HDT
---------	-------------	-----------------	----------------	----------------------	------------------	-----

ISOPHTHALIC / MARINE GRADE LAMINATING RESINS

UPPOL-3872TA-H40	ISOPHTHALIC, MEDIUM HIGH REACTIVE, THIXOTROPIC LAMINATING RESIN	500-700	1.2-1.5	PA	1.0	93
UPPOL-3872TA-LSE-H40	ISOPHTHALIC, MEDIUM HIGH REACTIVE, THIXOTROPIC, LSE, LAMINATING RESIN	400-600	1.2-1.5	PA	1.0	93
UPPOL-381-TA-LSE	ISO/NPG, HIGH REACTIVE, THIXOTROPIC, HIGH MOL. WT. LAMINATING	850-950	1.1-1.3	PA	1.0	103

* REFER TO TECHNICAL DATA SHEET FOR METHODS

PA + PRE-ACCELERATED

HDT : METHOD ISO 0075-B